

Patent [19]

[11] Patent Number: 08059940

[45] Date of Patent: Mar. 05, 1996

[54] ELECTROCONDUCTIVE FLUORORUBBER COMPOSITION FOR CROSSLINKING AND MOLDING THEREFROM

[21] Appl. No.: 06222580 JP06222580 JP

[22] Filed: Aug. 23, 1994

[51] Int. Cl.⁶ C08L02712 ; C08K00304; C08K00514; C08K00517; C08K00550

[57] ABSTRACT

PURPOSE: To obtain the subject composition excellent in electrical conductivity and capable of providing a crosslinked coating film having low viscosity, low hardness, etc., by blending iodine and/or a bromine-containing fluororubber with an onium salt compound, an electroconductive filler, a crosslinking agent and a peroxide compound at a specific ratio.

CONSTITUTION: This composition is obtained by blending (A) 100 pts. wt. of an iodine- and/or bromine-containing fluororubber with (B) preferably 0.1-20 pts.wt. of an onium salt compound of the formula (R⁹ is a 1-20C alkyl, allyl, etc.; R¹⁰ to R¹² are each an aryl or a substituted aryl; A is an anion such as a halide, a sulfate or a sulfite), (C) 1-20 pts.wt. of an electroconductive filler (preferably 30-400ml/100g as DBP oil absorbing amount) (D) 0.1-10 pts.wt. of a crosslinking agent, (E) 0.1-10 pts.wt. of a peroxide compound. The electroconductive fluororubber molding is obtained by foaming, crosslinking and molding a composition containing (F) a foaming agent in addition to the above components of the composition. The electroconductive fluororubber molding is preferably a coating film having 40-50Hs (Type C) hardness and 10⁶ to 10¹¹ &mega; resistance.

* * * * *

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 08-059940

(43)Date of publication of application : 05.03.1996

(51)Int.Cl.

C08L 27/12
C08K 3/04
C08K 5/14
C08K 5/17
C08K 5/50

(21)Application number : 06-222580

(71)Applicant : DAIKIN IND LTD

(22)Date of filing : 23.08.1994

(72)Inventor : MATSUMOTO KOJI

UEDA YUTAKA

TOMOTA MASAYASU

(54) ELECTROCONDUCTIVE FLUORORUBBER COMPOSITION FOR CROSSLINKING AND MOLDING THEREFROM

(57)Abstract:

PURPOSE: To obtain the subject composition excellent in electrical conductivity and capable of providing a crosslinked coating film having low viscosity, low hardness, etc., by blending iodineand/or a bromine-containing fluororubber with an onium salt compound, an electroconductive filler, a crosslinking agent and a peroxide compound at a specific ratio.

CONSTITUTION: This composition is obtained by blending (A) 100 pts. wt. of an iodine- and/or bromine-containing fluororubber with (B) preferably 0.1-20 pts.wt. of an onium salt compound of the formula (R9 us a 1-20C alkyl, allyl, etc.; R10 to R12 are each an aryl or a substituted aryl; A is an anion such as a halide, a sulfate or a sulfite), (C) 1-20 pts.wt. of an electroconductive filler (preferably 30-400ml/100g as DBP oil absorbing amount) (D) 0.1-10 pts.wt. of a crosslinking agent, (E) 0.1-10 pts.wt. of a peroxide compound. The electroconductive fluororubber molding is obtained by foaming, crosslinking and molding a composition containing (F) a foaming agent in addition to the above components of the composition. The electroconductive



fluororubber molding is preferably a coating film having 40-50Hs (Typec) hardness and 106 to 1011 Ω resistance.

LEGAL STATUS

[Date of request for examination] 30.06.1999

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number] 3312501

[Date of registration] 31.05.2002

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office

(19) 日本国特許庁 (J P)

(12) 公開特許公報 (A)

(11) 特許出願公開番号

特開平8-59940

(43) 公開日 平成8年(1996)3月5日

(51) Int.Cl. ⁸	識別記号	庁内整理番号	F I	技術表示箇所
C 0 8 L 27/12	K J M			
C 0 8 K 3/04	K J F			
5/14	K F Y			
5/17	K J K			
5/50				

審査請求 未請求 請求項の数9 F D (全 9 頁)

(21) 出願番号	特願平6-222580	(71) 出願人	000002853 ダイキン工業株式会社 大阪府大阪市北区中崎西2丁目4番12号 梅田センタービル
(22) 出願日	平成6年(1994)8月23日	(72) 発明者	松本 幸治 大阪府摂津市西一津屋1-1 ダイキン工業株式会社淀川製作所内
		(72) 発明者	植田 豊 大阪府摂津市西一津屋1-1 ダイキン工業株式会社淀川製作所内
		(72) 発明者	友田 正康 大阪府摂津市西一津屋1-1 ダイキン工業株式会社淀川製作所内
		(74) 代理人	弁理士 田村 巖

(54) 【発明の名称】 架橋用導電性フッ素ゴム組成物及び成形品

(57) 【要約】

【目的】 優れた導電性を有し、組成物の粘度が低く、且つ低硬度で抵抗値も安定している架橋被膜を与えるフッ素ゴム組成物及びこの組成物を用いて得られる導電性フッ素ゴム成形品を提供する。

【構成】 ヨウ素及び／又は臭素含有フッ素ゴム 100重量部に対して、オニウム塩化合物 0.1～20重量部、導電性フィラー 1～20重量部、架橋剤 0.1～10重量部、パーオキサイド化合物 0.1～10重量部を配合したことを特徴とする架橋用導電性フッ素ゴム組成物及びこれより得られる導電性フッ素ゴム成形品。